

Test Report

No. AJHL1608009434FB

Date: SEP.02, 2016

Page 1 of 3

SHAOXING BIGU TEXTILES CO., LTD

NO.75 ZHENYUAN ROAD PAOJIANG SHAOXING

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: IFR POLY KNIT

Color: BLACK

Composition: 100% POLYESTER

Manufacturer: SHAOXING BEGOOD TEXTILES CO., LTD

Test Requested:

Determine the flame resistance in accordance with test method 1 of NFPA 701:2015 Standard Methods of Fire Tests for Flame Propagation of Textiles and Films

Test Results: -- See attached sheet --

Conclusion: The tested sample "As received" **meets** the requirements of Test Method 1 of NFPA 701:2015.

Test Period:

Sample Receiving Date : AUG.26, 2016

Test Performing Date : AUG.26, 2016 TO AUG.31, 2016

Signed for and on behalf of
SGS-CSTC Co., Ltd. Anji Branch



Allen Zou
Technical Manager



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Anji Branch

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Report

No. AJHL1608009434FB

Date: SEP.02, 2016

Page 2 of 3

I. Test Conducted

This test was conducted in accordance with test method 1 of NFPA 701:2015 Standard Methods of Fire Tests for Flame Propagation of Textiles and Films.

II. Details of tested sample

Sample description / Color	IFR POLY KNIT / Black
Area density	About 119 g/m ²
Products configuration	Single Layer
Size of sample *	150mm × 400mm 10pcs

* With the length parallel to the lengthwise direction of the material

III. Conditioning

Prior to testing, the sample was conditioned at least 30 minutes at 105°C±3°C (220°F±5°F)

IV. Test results

Specimen No.	Mass before test (g)	Mass after test (g)	Mass loss (%)	After flame time (s)	Burning time on floor (s)
1	7.51	6.22	17.18	0	0
2	7.43	5.79	22.07	0	0
3	7.52	5.92	21.28	0	0
4	7.40	7.04	4.86	0	0
5	7.46	6.41	14.08	0	0
6	7.41	6.03	18.62	0	0
7	7.50	6.16	17.87	0	0
8	7.46	6.36	14.75	0	0
9	7.53	6.47	14.08	0	0
10	7.47	6.31	15.53	0	0
Mean	7.47	6.27	16.03	0	0

SD =4.83 3SD =14.49 Mean + 3SD =30.52

SD – Standards deviation

To be continued....



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Report

No. AJHL1608009434FB

Date: SEP.02, 2016

Page 3 of 3

Observations:

Vigorousness of burning	No
Material molten dripping	Yes
Odor smoke	Yes

Criteria for test method 1 (Chapter 10):

1. Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimen.
2. The average weight loss of the 10 specimen in a sample shall be 40 percent or less.
3. No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
4. When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.
5. When a sample does not demonstrate passing performance in accordance with all of the conditions indicated above, the material shall be recorded as having failed Test Method 1.

Photo Appendix:



SGS authenticate the photo on original report only

*** End of Report ***