



中国认可
国际互认
检测
TESTING
CNAS L4743

Test Report

No. AJFS2011009764FF

Date: NOV.18, 2020

Page 1 of 3

QATAR TRUST SOLUTIONS

#128, FIRST FLOOR, REGUS, BLDG, D-RING ROAD, P. O. BOX-24277 DOHA, QATAR

The following sample(s) information was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

Sample Description: INHERENT FLAME RETARDANT BLACKOUT FABRIC

Color: BURGUNDY

Style/Item No.: /

Composition: 100% POLYESTER

Supplier: SHAOXING BEGOODTEX CO., LTD.

Test Requested:

NFPA 701:2019 Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, test method 1.

Test Results: -- See attached sheet --

Conclusion:

The tested sample "As received" **meets** the requirements of NFPA 701:2019, test method 1.

Test Period:

Sample Receiving Date : NOV.11, 2020

Test Performing Date : NOV.11, 2020 TO NOV.17, 2020

Signed for and on behalf of
SGS-CSTC Co., Ltd. Anji Branch

Allen Zou
Lab Manager

scan to see the report



AJFS2011009764FF



SGS-CSTC 检测技术有限公司
Anji Branch Fire Technology Service

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编: 313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

Test Report

No. AJFS2011009764FF

Date: NOV.18, 2020

Page 2 of 3

I. Test Conducted

This test was conducted in accordance with test method 1 of NFPA 701:2019 Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, test method 1.

II. Details of tested sample

Sample description / Color	Fabric / Burgundy
Area density	About 267 g/m ²
Products configuration	Single Layer
Size of sample *	400 mm × 150mm
Exposed surface	Any surface

* With the length parallel to the lengthwise direction of the material

III. Conditioning and cleaning procedure

Cleaning procedure: none

Prior to testing, the sample was: [☒] Dried in oven at 105°C±3°C for 30 minutes.

[☐] Conditioned at 20°C±5°C for 24 hours.

IV. Test results

Specimen No.	Mass before test (g)	Mass after test (g)	Mass loss (%)	After flame time (s)	Burning time on floor (s)
1	16.62	13.16	20.82	0	0
2	16.62	13.57	18.35	0	0
3	16.89	14.20	15.93	0	4.5
4	16.73	13.38	20.02	0	2.4
5	16.61	14.05	15.41	0	1.7
6	16.88	13.76	18.48	0	2.8
7	16.93	13.91	17.84	0	0
8	16.75	14.12	15.70	0	4.1
9	16.69	13.68	18.03	0	0
10	16.84	13.72	18.53	0	0
Average	16.76	13.76	17.91	0	1.6

SD =1.79 3SD =5.37 Mean + 3SD =23.28

SD – Standards deviation

To be continued....



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Test Report

No. AJFS2011009764FF

Date: NOV.18, 2020

Page 3 of 3

Observations:

Vigorousness of burning (Yes / No)	No
Material molten dripping (Yes / No)	Yes
Odor smoke (Yes / No)	Yes

Criteria for test method 1 (Chapter 10):

1. Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens.
2. The average weight loss of the 10 specimens in a sample shall be 40 percent or less.
3. No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
4. When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.
5. When a sample does not demonstrate passing performance in accordance with all of the conditions indicated above, the material shall be recorded as having failed Test Method 1.

Statement: This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

Photo Appendix:



SGS authenticate the photo on original report only

*** End of Report ***



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC (Shanghai) Inspection & Testing Services Co., Ltd.
Anji Branch Fire Technology Service

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejiang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgs.com.cn
中国·浙江·安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com

Member of the SGS Group (SGS SA)